

PŘEVODNÍ TABULKA

norem šedých a tvárných litin

ZEMĚ	STANDARD			STANDARD		
	UNIBAR 200	UNIBAR 250	UNIBAR 300	UNIBAR 400-15	UNIBAR 500-7	UNIBAR 600-3
EN	GJL-200	GJL-250	GJL-300	GJS-400-15	GJS-500-7	GJS-600-3
Česká republika	422420	422425	422430	422304	422305	422306
	422418	422424	422428	422442	422450	422460
Velká Británie	Gr.180/200	Gr.260	Gr.300	400/12	500/7	600/3
Australie	T-200	T-250	T-300	400-12	500-7	600-3
Belgie	NBN830-01	FGG25	FGG30	FNG42-12	FNG50-7	FNG60-2
Dánsko	DS 11301	GG 25	GG 30	0715-0716	727	707
Finsko	SFS 4855	GRS250	GRS300	GRP400	GRP500	GRP600
Francie	NF A32-101	FGL250	FGL300	FGS400-15	FGS500-7	FGS600-3
Holandsko	NEN 6002A	GG 25	GG 30	GN 42	GN 50	GN 60
Itálie	UNI 5007	G 25	G 30	GS400-12	GS500-7	GS600-3
Japonsko	JIS.G5501	FC 25	FC 30	FCD40	FCD50	FCD60
Jugoslávie	JuseC.J2020	SL 25	SL 30	NL42	NL50	NL60
Maďarsko	MSZ 8280	öV 250	öV 300	Göv 400	Göv 500	Göv 600
Německo	DIN 1691	GG 25	GG 30	GGG 40	GGG 50	GGG 60
Norsko	NS 722	SjG 25	SjG 30	NS 11342	NS 11350	NS 11360
Polsko	PNH-83101	ZI 250	ZI 300	Zs40012	Zs50007	Zs60003
Portugalsko	NP 1758	FGL-250	FGL-300	FGE 400/12	FGE 500/7	FGE 600/3
Rakousko	M3191	GG-25	GG-30	GGG-400	GGG-500	GGG-600
Rumunsko	S T A S 568	FC 250	FC 300	FGN400-12	FGN500-7	FGN600-3
Rusko	GOST 1412	SC 25	SC 30	Vch40	Vch50	Vch60
Španělsko	U N E 36-111	FG 25	FG 30	FGE 42-12	FGE 50-7	FGE 60-2
Svédsko	MNC 705E	SSOI 25-00	SSOI 30-00	SSO7 17-00	SSO7 27-02	SSO7 32-03
Švýcarsko	VSM 10691	FGL 250	FGL 300	FGS42	FGS50	FGS60
USA 1983	ASTM A48	Class 25	Class 40	65-45-12	70-50-07	80-60-03
Meehanite	GE200	GD250	GB300	SF420.12	SFP500	SFP600
ISO 1961	Gr.20	Gr.25	Gr.30	Gr.400-12	Gr.500-7	Gr.600-3